



Test Results | THERMORY® White Ash Rot Resistance

Rot
Resistance

TESTED

► Fungus spores were introduced to THERMORY® White Ash samples to promote fungal growth over a period of time, along with control samples, mass loss was then calculated to interpolate the class of rot resistance per European standards.

RESULTS

► We achieved Durability Class 1, which means that on average, the THERMORY® White Ash cladding or decking will last outdoors for at least 25 years or more with minimal maintenance or added oils.



► DECKING ► CLADDING ► PORCH FLOORING

ThermoryUSA.com support@thermoryusa.com

BUFFALO

P: 585.250.4074 • F: 847.256.0509
56 Harvester Avenue, Suite 1-201
Batavia, NY 14020

DENVER

P: 720.759.7268 • F: 847.256.0509
537 W. Highlands Ranch Pkwy, Unit #114
Highlands Ranch, CO 80129



TEST REPORT

307874 / 1

Revision: 0
Date of receipt: 08/03/21
Date of test: 29/03/21
Date of issue: 06/09/21


Sample name: Thermory ash

THERMORY AS
LOOTSA 1A
11415 TALLINN
EE - ESTONIA

Durability of wood. Assessment of inherent or enhanced durability against wood-destroying basidiomycetes EN 113-2:2020

Timber species:	heat treated ash (as declared by the orderer)
Origin:	not specified
Description of timber:	not applicable
Sampling:	done by the orderer
Density of timber:	689 kg/m ³
Reference timber species:	Pinus sylvestris; Fagus sylvatica
Ageing procedure applied:	none
Method of sterilisation:	gamma irradiation (25kGy)
Species and strain number of test fungi:	Coniophora puteana DSM 3085; Trametes versicolor DSM 3086
Duration of exposure to fungi:	from 11/05/2021 to 31/08/2021
Mean mass loss of reference timber:	see Table 1
Median mass loss of test timber:	see Table 3
Provisional durability class according to this standard:	DC1 - very durable
Officer in charge of testing:	Dr. Elena Conti
Notes:	- The interpretation and practical conclusions that can be drawn from this test report require a specific knowledge of timber.

This test report is part of a PDF file digitally signed by Franco Bulian on 07/09/21.

The managing director
Dr. Franco Bulian


The sample name and, when relevant, its description, are given by the orderer, and CATAS does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise required by standards and technical specifications or agreed with the customer, any declarations of conformity made by CATAS are based on the comparison between results and reference values, where the confidence intervals of the measures are not taken into account. Unless otherwise stated, sampling is made by the customer; in this case the test results are referred to the sample as received.

TEST REPORT

307874 / 1 rev. 0

Date of issue:

06/09/21

Sample name:

Thermory ash

Table 1

Percentage mass loss of the reference test specimens (% m/m)

Pinus sylvestris with Coniophora puteana		Fagus sylvatica with Trametes versicolor	
1	28,40	1	28,73
2	29,19	2	27,69
3	26,18	3	19,64
4	32,49	4	24,70
5	32,98	5	24,46
6	27,30	6	25,63
7	28,66	7	19,73
8	25,93	8	30,19
9	34,51	9	20,69
10	32,01	10	23,98
mean	29,76	mean	24,54

Note on test validity: the mass loss values meet the validity criteria of the test


Table 2

Moisture content of the test specimens after exposure to the fungi (% m/m)

Coniophora puteana		Trametes versicolor	
mean	33,80	mean	35,87
lowest	25,3	lowest	20,72
highest	47,97	highest	59,75

This test report is part of a PDF file digitally signed by Franco Bulian on 07/09/21.

The managing director
Dr. Franco Bulian



TEST REPORT

307874 / 1 rev. 0

Date of issue:

06/09/21

Sample name:

Thermory ash

Table 3

Percentage mass loss of the test specimens (% m/m)

Coniophora puteana		Trametes versicolor	
1	-0,40	1	-0,40
2	0,77	2	0,77
3	-0,16	3	-0,16
4	-0,24	4	-0,24
5	-0,32	5	-0,32
6	0,16	6	0,16
7	0,23	7	0,23
8	0,30	8	0,30
9	-0,08	9	-0,08
10	0,55	10	0,55
11	-0,49	11	-0,49
12	0,96	12	0,96
13	0,09	13	0,09
14	0,88	14	0,88
15	0,31	15	0,31
16	1,20	16	1,20
17	-0,48	17	-0,48
18	0,00	18	0,00
19	0,87	19	0,87
20	-0,08	20	-0,08
21	0,07	21	0,07
22	0,43	22	0,43
23	-0,66	23	-0,66
24	-0,08	24	-0,08
25	-0,65	25	-0,65
26	-0,08	26	-0,08
27	0,24	27	0,24
28	0,26	28	0,26
29	0,00	29	0,00
30	0,86	30	0,86
median	0,08	median	0,93

This test report is part of a PDF file digitally signed by Franco Bulian on 07/09/21.

The managing director
Dr. Franco Bulian
